


Amendments to the Claims

1. (Original) Organic acid anion containing aluminum salt hydroxide particles represented by the following general formula (I):



(wherein M is at least one cation selected from the group consisting of Na^+ , K^+ , NH_4^+ and H_3O^+ , M' is at least one metal cation selected from the group consisting of Cu^{2+} , Zn^{2+} , Ni^{2+} , Sn^{4+} , Zr^{4+} , Fe^{2+} , Fe^{3+} and Ti^{4+} , A is at least one organic acid anion, B is at least one inorganic acid anion, and a, b, m, n, x, y and z satisfy $0.7 \leq a \leq 1.35$, $2.7 \leq b \leq 3.3$, $0 \leq m \leq 5$, $4 \leq n \leq 7$, $0 \leq x \leq 0.6$, $1.7 \leq y \leq 2.4$, and $0.001 \leq z \leq 0.5$, respectively.)

2. (Original) The particles according to claim 1, which are represented by the formula (I) wherein a satisfies $0.9 \leq a \leq 1.2$.

3. (Original) The particles according to claim 1, which are represented by the formula (I) wherein b satisfies $2.8 \leq b \leq 3.2$.

4. (Original) The particles according to claim 1, which are represented by the formula (I) wherein m satisfies $0 \leq m \leq 2$.

5. (Original) The particles according to claim 1, which are represented by the formula (I) wherein n satisfies $5 \leq n \leq 6.5$.

6. (Original) The particles according to claim 1, which are represented by the formula (I) wherein x satisfies $0 \leq x \leq 0.3$.

7. (Original) The particles according to claim 1, which are represented by the formula (I) wherein y satisfies $1.8 \leq y \leq 2.2$.

8. (Original) The particles according to claim 1, which are represented by the formula (I) wherein z satisfies $0.01 \leq z \leq 0.4$.

9. (Original) The particles according to claim 1, wherein the organic acid anion (A) in the formula (I) is at least one selected from anions based on an organic carboxylic acid and an organic oxycarboxylic acid.

10. (Original) The particles according to claim 1, wherein the organic acid anion (A) in the formula (I) is at least one selected from anions based on an organic carboxylic acid and an organic oxycarboxylic acid which have 1 to 15 carbon atoms.

11. (Original) The particles according to claim 1, wherein the inorganic acid anion (B) in the formula (I) is at least one selected from the group consisting of a sulfate ion, a phosphate ion, a nitrate ion and a silicate ion.

12. (Original) The particles according to claim 1, wherein the inorganic acid anion (B) in the formula (I) is a sulfate ion or a sulfate ion and a phosphate ion.

13. (Original) The particles according to claim 1, wherein D_{25} and D_{75} satisfy $1 < D_{75}/D_{25} < 1.8$ when particle diameters at 25% and 75% values of cumulative particle size distribution curve measured by a laser diffraction method are represented by D_{25} and D_{75} , respectively..

14. (Original) The particles according to claim 1, which are in the shape of grains, pairs, rectangular parallelepiped, disks (go stones), hexagonal plates, rice grains or cylinders.

15. (Original) The particles according to claim 1, having an average particle diameter of 0.1 to 10 μm .

16. (Withdrawn) A burned product obtained by burning the organic acid anion containing aluminum salt hydroxide particles of claim 1 at 300 to 1,000°C.

17. (Original) The particles according to claim 1, which carry a hydrolysate of a salt of at least one metal selected from the group consisting of Cu, Zn, Ni, Sn, Zr, Fe and Ti, on the surfaces thereof.

18. (Withdrawn) The alunite type compound particles of claim 1, having surfaces thereof treated with at least one surface treating agent selected from the group consisting of a higher fatty acid, an anionic surfactant, a phosphoric ester, a coupling agent and an ester of a polyhydric alcohol and a fatty acid.

19. (Canceled)

20. (Currently Amended) The method according to claim ~~19~~30, wherein the inorganic salt is aluminum sulfate.

21. (Currently Amended) The method according to claim ~~19~~30, wherein the organic acid is at least one selected from the group consisting of an organic carboxylic acid, an organic oxycarboxylic acid and their salts.

22. (Currently Amended) The method according to claim ~~19~~30, wherein the organic acid is at least one selected from the group consisting of an organic carboxylic acid having 1 to 15 carbon atoms, an organic oxycarboxylic acid having 1 to 15 carbon atoms, and their salts.

23. (Currently Amended) The method according to claim ~~19~~30, wherein the inorganic acid salt is at least one selected from the group consisting of a sulfate, a nitrate, a phosphate and a silicate.

24. (Currently Amended) The method according to claim ~~19~~30, ~~comprising carrying out~~ wherein the heating reaction is carried out at 90 to 250°C.

25. (Withdrawn) A resin additive comprising the organic acid anion containing aluminum salt hydroxide particles of claim 1.

- 26. (Withdrawn)** A resin composition containing the resin additive of claim 25.
- 27. (Withdrawn)** An adsorbent composition containing the organic acid anion containing aluminum salt hydroxide particles of claim 1.
- 28. (Withdrawn)** A dye carrier containing the organic acid anion containing aluminum salt hydroxide particles of claim 1.
- 29. (Withdrawn)** An ultraviolet absorber containing the organic acid anion containing aluminum salt hydroxide particles of claim 1.
- 30. (New)** A method for producing organic acid anion containing aluminum salt hydroxide particles, which comprises adding an alkali hydroxide solution selected from the group consisting of Na^+ , K^+ , NH_4^+ and H_3O^+ to a mixed solution comprising an organic acid or organic acid salt, an inorganic salt of Al^{3+} , and a sulfate or nitrate of at least one member selected from the group consisting of Na^+ , K^+ , NH_4^+ and H_3O^+ to cause a heating reaction.
- 31. (New)** The method according to claim 30, wherein the mixed solution further comprises an inorganic salt of at least one cation selected from the group consisting of Cu^{2+} , Zn^{2+} , Ni^{2+} , Sn^{4+} , Zr^{4+} , Fe^{2+} , Fe^{3+} and Ti^{4+} .
- 32. (New)** The method according to claim 31, wherein the inorganic salt is aluminum sulfate.
- 33. (New)** The method according to claim 31, wherein the organic acid is at least one selected from the group consisting of an organic carboxylic acid, an organic oxycarboxylic acid and their salts.

34. (New) The method according to claim 31, wherein the organic acid is at least one selected from the group consisting of an organic carboxylic acid having 1 to 15 carbon atoms, an organic oxycarboxylic acid having 1 to 15 carbon atoms, and their salts.

35. (New) The method according to claim 31, wherein the inorganic acid salt is at least one selected from the group consisting of a sulfate, a nitrate, a phosphate and a silicate.

36. (New) The method according to claim 31, wherein the heating reaction is carried out at 90 to 250°C.